

16 oz. STAINLESS/WHITE TUMBLER w/HANDLE

XP8261, XP8262

Standard Mug Press Process

Time: 2 minutes

Temperature: 356° F

Pressure: Light (excessive pressure will damage)



Oven Process

Time: 6.5 minutes Temperature: 350° F Pressure: SubWrap 3

Fabrication Process

- Remove lid.
- Affix the transfer to the product using heat tape.
- Place sacrificial paper over the transfer. Place in mug press. (or use SubWrap3)
- After appropriate cure time, remove from press and set aside to cool. Water bath can be used for faster cooling.

Note: Use caution when removing from oven. Product will be extremely hot.

