TECH T

STAINLESS STEEL WINE GLASS (120z.)

DW2W20 - White Stainless Steel

Settings

Time: 2 minutes

Temperature: 375° F

Pressure: Heavy

Supplies

JP Sublimation Paper | Silicone Wrap | Mug Press or Convection Oven

Sublimation Process

- Preheat mug press to 375° F while preparing product.
- Position artwork and use thick mug wrap for pressing.
- Press for 2 minutes w/ heavy pressure.
- If using a **convection oven**, preheat to 375° F while preparing product.
- Use silicone wrap to hold and press transfer onto glass, apply pressure.
- Heat in oven for 7 minutes.
- Use protective glove to remove as product will be extremely hot.
- Remove silicone & transfer.

Heat Transfer Process

- Preheat mug press to 320° F while preparing product.
- Use Magic Touch Hard Surface CPM 6.2 paper for transfer.
- Position artwork and use tapered insert w/stopper to press glass.
- Press for 2 minutes with moderate to heavy pressure.
- Peel warm.







