

Silver 9"x13" Cake Pan

JOHNSON PLASTICS
PLUS

SILVER 9"x13" CAKE PAN- Sublimation

SUBCP



GENERAL SUBLIMATION PROCESS

Recommended Equipment & Accessories

- Sublimation Printer
- Standard Flat Heat Press- Swing-away style press recommended
- Heat Tape
- Teflon sheet or Blowout paper
- Heat gloves
- **REQUIRED:** SUBCPPADSET

Recommended Settings	
Time	50-60 seconds
Temperature	390-400°F
Pressure	Medium

General Sublimation Instructions

- Preheat the heat press to around 390-400°F. Set the time to 50-60 sec., set pressure to medium.
- Attach the printed transfer to the cake pan lid using heat tape.
 - For best results, utilize the product template for the cake pan lid, found on SUBCP product page on JPPlus.com.
 - When placing the image on the cake pan lid, note the cake pan logo on the side. For best image quality results, avoid sublimating over top of the logo.
- Place blowout paper or Teflon sheet onto the heat press platen.
- **REQUIRED:** Place the support pads (SUBCPPADSET) for the cake pan top onto the blowout paper.
- Place the cake pan lid blank with attached transfer onto the sheet, with transfer on top.
- Place another piece of blowout paper or Teflon sheet on top of the transfer sheet.
- Close and press for recommended time.
- When finished, open heat press and use heat gloves to remove the paper transfer and allow the cake pan lid to cool.

Tips and Tricks

- For best image placement, utilize the product template found on the product page on JPPlus.com.

Troubleshooting

- The image came out light and/or faded.
 - The time setting may need to be increased.
 - The temperature setting may need to be increased.
 - The pressure setting on the press or wrap may be too light and need to be increased for better contact between the sublimation transfer paper and the surface of the product.
 - The press or oven may not be heating at the temperature set on the display.
 - The sublimated image may have been printed on the wrong side of the sublimation paper.
- The image colors are dull on the sublimated product.
 - The press/heat time may need to be decreased.
 - The press/heat temperature may need to be decreased.

- The print settings may need to be adjusted. Also check that the proper paper type and/or color profile is selected before printing the image.
 - The image colors are not correct on the sublimated product.
 - The print settings may need to be adjusted. Also check that the proper paper type and/or color profile is selected before printing the image.
 - Convert the colors used in the image to RGB color mode in the design/layout software before printing.
 - If spot colors are used in the image (common for logos), convert the spot colors to RGB color mode in the design/layout software before printing.
 - The sublimation paper is brown and sticking to the product.
 - The press/heat time may need to be decreased.
 - The press/heat temperature may need to be decreased.
 - The pressure setting may need to be decreased.
 - Use of a different sublimation paper brand or type may be needed for the particular product.
 - The sublimated image appears blurry or fuzzy.
 - The pressure setting may need to be increased.
 - The sublimation transfer paper may need to be secured to the product to prevent the paper from moving.
 - The sublimatable surface of the product may be defective.
-

Templates and Images

- Visit jpplus.com to find the product page for this item. The product template may be found under the Tech Docs and Downloads area of the page.
-

To order more of this product, see similar products and much more, please visit jpplus.com.

For additional product support and troubleshooting, please contact JPPlus Advanced Support Team:

- Phone: 419-500-4877
- Email: ast@jpplus.com
- Schedule an appointment: <https://jpplusadvancedsupport.setmore.com/>