

## IMAGE MAKER SUBLICOAT ALUMINUM BLANKS

IM13AL8002 | IM13AL6002

Sublcoat blanks provide high quality sublimation results at an economical price.

### Equipment

- SG800 Printer
- JPP Sublimation Paper
- DK20 Heat Press

### Sublimation Process

- Print image onto JPP paper.
- Place blow out paper on press bed.
- Center image over top of blanks. Cover material and transfer with a piece of silicone tissue paper.
- Press in the heat press at 390°F for 45 - 50 seconds using med.- heavy pressure.
- Lift heat press and remove all components from the press.
- Remove transfer immediately.

**Note:** Processes noted above are intended as safe guidelines and may need minor adjustments to achieve optimal results.