

TERRYTOWN COLLECTION

These products offer a stunning combination of comfort and elegance to personalize for your home or treasured gift giving.

Settings

- **Time:** 35 seconds
- **Temperature:** 405° F
- **Pressure:** 40 psi

Fabrication Process

- Place blowout paper on heat press platen.
- Place product with attached transfer sheet on top of blowout paper. Transfer sheet should be on top.
- Adjust press pressure to 40 psi. Close press.
- Press for recommended time. When finished, open press and remove the product. Remove transfer sheet and discard.

Note: These recommendations are offered in conjunction with manufacturer's settings. Due to variations in equipment and shop conditions, minor adjustments may be needed to achieve optimal results.